546

湿法短切原丝WCS

Wet Chopped Strands (WCS)

产品说明 *Product Description*

湿法短切原丝 546 用连续纤维短切一定长短而成，主要用于石膏工业。

546 Wet Chopped Strands are formed by chopping continuous fibers to a certain length, mainly used in the gypsum industry.



产品特点 *Product Features*

◎ 在石膏中有快速均匀的分散性
◎ 连续的流动性
◎ 在最终制品中有优良的性能
◎ 优异的耐腐蚀性能

·Fast and uniform dispersion in gypsum
·Good flowability
·Excellent properties in composite products
·Excellent corrosion resistance

规格代号 *Specification*

玻璃类型 *Glass type*	*E*		
短切原丝 *Chopped strands*	*CS*		
典型纤维直径 *Typical filament diameter (μm)*	*11*	*13*	*16*
典型短切长度 *Typical chopped length (mm)*	*3* *6*		
示例 *Example*	*ECS11-03-546*		

技术指标 *Technical Parameters*

项目 *Item*	纤维直径偏差 *Filament diameter variation*	含水率 *Moisture content*	可燃物含量 *Sizing content*	短切长度偏差 *Chopped length variation*	短切率 *Choppability*
单位 *Unit*	*%*	*%*	*%*	*mm*	*%*
检测方法 *Test method*	*ISO 1888*	*ISO 3344*	*ISO 1887*	*Q/JS J0361*	*Q/JS J0362*
巨石标准 *Jushi standard*	*± 10*	*10.00 ± 2.00*	*≤ 0.10*	*± 1.00*	*≥ 99.00*
行业标准 JC/T 896 *Industry standard*	*± 15*	WCS无标准 *No standard*	WCS无标准 *No standard*	*± 1.5*	*≥ 95*

使用说明 *Instructions*

◎ 本产品在3个月内使用最佳，使用前应保存在原包装内。
◎ 产品使用时注意防护，避免产品擦毛、损伤等情况。
◎ 使用前调理纱线的温湿度与环境温湿度平衡，使用时对环境温湿度进行适当控制。

·The product is best used within 3 months after production, and should be kept in the original package before use.
·Care should be taken when using the product to prevent it from being scratched or damaged.
·The temperature and humidity of the product should be conditioned to be close or equal to the ambient temperature and humidity before use, and the ambient temperature and humidity should be properly controlled during the use.

包装信息 *Packaging*

采用集装袋包装、塑料袋包装：

- 集装袋可装900kg～1200kg产品，标准定重1000kg。
- 塑料袋可装15kg～30kg产品，标准定重25kg。

The product can be packed in container bags or plastic bags:

- A container bag can hold 900kg～1200kg of products, with the standard weight being 1000kg.

- A plastic bag can hold 15kg～30kg of products, with the standard weight being 25kg.

包装图片 *Package picture*





集装袋尺寸 *Container bag size*

长度 *Length mm(in)*	*900 (35.43)*
宽度 *Width mm(in)*	*900 (35.43)*
高度 *Height mm(in)*	*1100 (43.31)*

贮 存 *Storage*

在没有特殊要求的情况下，玻璃纤维产品应贮存在干燥、阴凉的地方，防止受潮。最佳存储条件为温度 0℃～ 35℃，相对湿度≤80%。为确保安全，避免损坏产品，托盘的堆码高度不应超过三层。当堆放两层或三层高时，要求正确地、平稳地移动上面的托盘。

Unless otherwise specified, the fiberglass products should be stored in a dry,cool and moisture-proof area.The best temperature and humidity should be maintained at 0℃~35℃ and ≤80% respectively. To ensure safety and avoid damage to the product, the pallets should be stacked not more than three layers high. When the pallets are stacked in two or three layers, special care should be taken to correctly and smoothly move the upper pallet.

中国巨石股份有限公司 CHINA JUSHI CO.,LTD

Copyright © 2024 中国巨石股份有限公司，最终解释权归本公司所有。

地址：浙江省桐乡市梧桐街道凤凰湖大道318号，邮编：314500 *Add: 318 Fenghuanghu Avenue, Wutong District, Tongxiang, Zhejiang 314500, China*
(国内销售 *Domestic Sales*) 电 话 *Tel:+86-573-88181016* 传 真 *Fax:+86-573-88136248*
(国际销售 *International Sales*) 电 话 *Tel:+86-573-88136318* 传 真 *Fax:+86-573-88181058*
(客 服 *Customer Service*) 电 话 *Tel:+86-573-88136325* 传 真 *Fax:+86-573-88136248*
http://www.jushi.com *E-mail: info@jushi.com*